

# MADEIRA

## Technical Datasheet

09.09.2019

### LUNA

Article Description	Light-Storing & Emitting Embroidery Thread
Composition	Ca. 60% Polybutylenterephthalat / 40% Polypropylen
Count	dtex 150 x 2 / den 135 x 2
Make Up Available	750m Spool
Recommended needle size	75/11 – 80/12

### Mechanical – Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton)	DIN EN ISO 2062	ca.580cN
Elongation (% of stretch extension with weight tension until breaks)	DIN EN ISO 2062	ca.40%

### Recommendations for care



△ max. 20g/l active chlorine- max. 30°C - max. 30 min

### Oeko-Tex



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.